

PTFE D08 GF**Mechanical, Physical and Thermal Properties****glass + pigments + virgin PTFE**

properties	condition	standard	unit		unit	
colour				orange		orange
density/specific gravity	23 °C	DIN 53479	kg/m³	2230	g/cm³	2,23
hardness	23 °C	ISO 868	Shore D	62 ±3	Shore D	62 ±3
ball indentation hardness	23 °C	DIN 53456 H 135/30	MPa	24 ±5	psi	3480 ±725
tensile strength	23 °C	ASTM D 4745-79	MPa	≥ 26	psi	≥ 3770
elongation at break	23 °C	ASTM D 4745-79	%	300	%	300
compressive strength	23 °C	DIN 53455	MPa	≥ 8	psi	≥ 1160
thermal conductivity		DIN 52612	$\frac{J \cdot 10^3}{m \cdot h \cdot K}$	≥ 1,1	$\frac{J \cdot 10^3}{m \cdot h \cdot K}$	≥ 1,1
coefficient of thermal expansion	25 °C - 200 °C		$K^{-1} \cdot 10^{-5}$	≥ 10	$K^{-1} \cdot 10^{-5}$	≥ 10
coefficient of friction *	23 °C		μ	≥ 0,13	μ	≥ 0,13
minimum service temperature			°C	-200	°F	-328
maximum service temperature			°C	260	°F	500
young's modulus		DIN 53457	MPa		psi	

* coefficient of friction dry dynamic Steel 16MnCr5 v=0,6m/s; p=0,05 MPa; t=5h

Chemical Properties

Filled PTFE

Resistant to almost all chemicals

Not resistant to halogenides, elemental fluorine, CF₃, molten alkali metals

Foodstuff applications -